



MATERIAL DATA SHEET  
Material ref: CH1545  
Description: 45 duro Chlorobutyl

Typical Properties

<u>Property</u>	<u>Typical Value</u>
Hardness(shore A)	44
Tensile strength(PSI)	1210
Ultimate Elongation(%)	380
<b><u>Heat Resistance (70 hours @ 100C)</u></b>	
Hardness change(points)	+9
Tensile Change(psi)	-5
Elongation change(%)	-18
<b><u>Compression Set</u></b>	
22 hours @ 70C (%)	10
22 hours @ 100C (%)	32

*All data is derived from ASTM slabs. Values on actual parts will be somewhat different.*