



MATERIAL DATA SHEET

Material ref: CH1570
Description: 70 duro Chlorobutyl/FDA

Typical Properties

<u>Property</u>	<u>Typical Value</u>
Hardness(shore A)	70
Tensile strength(PSI)	1352
Ultimate Elongation(%)	335

Heat Resistance (70 hours @ 100C)

Hardness change(points)	+6
Tensile Change(psi)	-5
Elongation change(%)	-15

Compression Set

22 hours @ 70C (%)	9.5
22 hours @ 100C (%)	26

All data is derived from ASTM slabs. Values on actual parts will be somewhat different